# **Influence of solution hardening on microstructure and mechanical properties of Al-2.5Mg-0.7Li alloy**

# **Kozina, Franjo; Zovko Brodarac, Zdenka; Petrič, Mitja**

*Source / Izvornik:* **The 73rd World Foundry Congress, Congress Proceedings, 2018, 21 - 22**

**Conference presentation / Izlaganje na skupu**

*Permanent link / Trajna poveznica:* <https://urn.nsk.hr/urn:nbn:hr:115:742779>

*Rights / Prava:* [In copyright](http://rightsstatements.org/vocab/InC/1.0/) / [Zaštićeno autorskim pravom.](http://rightsstatements.org/vocab/InC/1.0/)

*Download date / Datum preuzimanja:* **2024-04-27**



*Repository / Repozitorij:*

[Repository of Faculty of Metallurgy University of](https://repozitorij.simet.unizg.hr) [Zagreb - Repository of Faculty of Metallurgy](https://repozitorij.simet.unizg.hr) [University of Zagreb](https://repozitorij.simet.unizg.hr)







# INFLUENCE OF SOLUTION HARDENING ON MICROSTRUCTURE AN AND MECHANICAL PRO OPERTIES OF Al-2.5 Mg-0.7Li ALLOY

# Franjo Kozina<sup>1</sup>, ZdenkaZovko Brodarac<sup>1</sup>, Mitja Petrič<sup>2</sup>

<sup>1</sup>University of Zagreb Faculty of Metallurgy, Alejanarodnihheroja 3, Sisak, Croatia<sup>,</sup> <sup>1</sup> University of Zagreb Faculty of Metallurgy, Alejanarodnihheroja 3, Sisak, Croatia<sup>.</sup><br>University of Ljubljana, Faculty of Natural Sciences and Engineering, Aškerčevacesta 12, Ljubljana, Slovenia <sup>2</sup> *\* \*Corresponding address: fkozin@simet.hr*

Key words: Al-2.5Mg-0.7Li alloy, solution hardening, microstructure, thermo-mechanical testing, mechanical properties

# ABSTRACT

Although utilization of lightweight aluminum alloys in transportation industry reduced harmful emissions and improves fuel economy, their further application is limited by low stiffness, low Young modulus and sensitivity to elevated temperatures. It was found that specific strength properties of aluminum alloys can be improved by Li additions. The beneficial effect is achieved by precipitation of hardening Al<sub>3</sub>Li precipitate.

The microstructural and mechanical properties of Al-2.5 Mg-0.7 Li alloy were investigated in as of Al-2.5 Mg-0.7 Li alloy were investigated in as cast and solution hardened condition. The microstructure constituents and thermo-mechanical properties for both conditions were determined and compared.

# 1. Introduction

Dependence of environmental conservation on transportation industry placed automotive manufacturers under great pressure to reduce fuel consumption and emissions. Weight reduction is considered to be the most cost-effective option to reduce harmful emissions and improve fuel economy [1]. The Al alloys were introduced as a response to the weight reduction demand. The downsizing effect of foundry Al-Si, Al Si, Al-Si-Cu, Al-Si-Mg alloysis achieved by precipitation of complex intermetallic phases [2]. to be the most cost-effective option to<br>termful emissions and improve fuel<br>1]. The Al alloys were introduced as a<br>o the weight reduction demand. The

However, the sensitivity to elevated temperatures[3], low Young modulus of elasticity and additional weight savings indicated the need for chemical composition redesign. Modifying chemical composition with Liadditions enables direct weight savings, improved elastic modulus and specific strength properties. The additions ofLi enable the formation of potent hardening precipitates, in particular metastable Al3Liprecipitate [4]. is achieved by precipitation of<br>
netallic phases [2].<br>
the sensitivity to elevated<br>
1], low Young modulus of elasticity<br>
weight savings indicated the need for<br>
mposition redesign. Modifying Solution in properties. The additions of<br>the properties. The additions of Linds<br>in order to the particular in the particular in the particular<br>of the condition in order to the particular in the particular<br>the condition in

An Al-2.5 Mg-0.7 Li alloy was investigated in as cast and solution hardened condition in order to compare microstructure and mechanical properties. The microstructure in as cast condition consists of following constituents: primary aluminum  $(\alpha_{\text{Al}})$ , intermetallic phases based on Li (metastable Al<sub>3</sub>Li and stabile AlLi phases), ternary phase(Al2LiMg) and secondary eutectic  $(A_3Mg_2)$ . Since the hardening is mainly achieved by precipitation of metastable Al3Li phase, solution hardening was used in order to dissolve other intermetallic precipitates and bulk  $\alpha_{Al}$  matrix. Identification of solution hardening parameters was performed based on thermodynamic behaviour of an alloy. mechanical testing, mechanical properties<br>is mainly achieved by precipitation of<br>example and phase, solution hardening was<br>order to dissolve other intermetallic<br>s and bulk  $\alpha_{Al}$  matrix. Identification of

# 2. Materials and methods and

The Al alloy was synthesized by melting in the induction melting furnace under protective induction melting furnace under protective<br>atmosphere of argon. The synthesized alloy was cast into a permanent steel mold without protective atmosphere.

In order to identify temperatures significant for<br>
recorder transformation and precipitations, phase transformation and precipitations Simultaneous Thermal Analysis(STA) was applied. The temperature of solution hardening The temperature of solution hardening<br>wasestimated on the base of Differential Scanning Calorimetry (DSC) results.The micro constituents Calorimetry (DSC) results. The micro constituents<br>in as cast condition were identified using X-Ray Diffraction (XRD).

Number of grains per unit area was determined for samples in in as cast condition, after solution hardening and after compression testing. Olympus SZ 11 with digital camera Promicra was used. Number of grains per unit area was determined<br>samples in in as cast condition, after solution<br>ening and after compression testing. Olympus

Thermo-mechanical properties were measured using Gleeble 1500D machine. Samples 1 and 2 were tested in as cast condition and at room temperature. The samples 3 and 4 were solution temperature. The samples 3 and 4 were solution hardened and tested at elevated temperatures. The micro-hardness was measured on samples in as cast condition and after solution hardening using LEICA VMHT 302801 machine. Thermo-mechanical properties were measured<br>using Gleeble 1500D machine. Samples 1 and 2<br>were tested in as cast condition and at room micro-hardness was measured on samples in as cast<br>condition and after solution hardening using LEICA<br>VMHT 302801 machine.<br>3. **Results and discussion**<br>The heat treatment regime consisted of<br>solution hardening at 520°C follo

## 3. Results and discussion

The heat treatment regime consisted of solution hardening at 520°C followed by quenching in water and artificial aging at 190°C during thermo-mechanical testing. rater and artificial aging at 190°C during<br>no-mechanical testing.<br>The number of grains pre unit area  $(N_A)$  is

given in Table 1.





The solution hardening led to the recrystallization of primary microstructure. The number of grains was reduced respectively. During thermo-mechanical testing of primary as cast microstructure, the number of grains significantly increased. In contrary, heat treated microstructure was not deformed at all during the same testing parameters.

The microstructure of samples before and after thermo-mechanical testing is given in Fig.1



*Fig. 1. The microstructure of:a) sample 1 - as cast;b) sample 2 – heat treated, c) sample 3 – as cast, thermomechanically tested, d) sample 4 – heat treated, thermomechanically tested.*

The thermo-mechanical testing of as cast microstructure (Fig.1a) led to the significant texture development (Fig.1c). Thermo-mechanical testing of solution hardened and aged microstructure (Fig.1b) did not causeanydirected microstructural change (Fig.1c).

The results of thermo-mechanical testing are given in Table 2.

Table 2. The results of thermo-mechanical testing

Sample No.	Strain rate, mm/min	Re, <b>MPA</b>	Rm, MPa	Deformation, $\frac{0}{0}$
	100	375.02	543.70	46.4
	230	155.17	289.89	41.5
	100	180.32	273.47	58.2
	100	178.20	260.17	55.3

The sample 1 had the highest tensile and yield strength values. Increasing strain rate up to 230 mm/min caused the drop in both values (sample 2). Samples 3 and 4 had a significantly lower strength properties compared to the first two samples. It is assumed that higher strength properties in as cast condition occurred as a result of  $Al<sub>3</sub>Li$  precipitates. These Li based intermetallic precipitates interact with dislocations progressing from the grain boundaries. The assumption is supported by texture development during thermo-mechanical testing (Fig.1b). The solution hardening caused dissolution of Al3Li precipitates enabling free movement of

dislocations. Furthermore, the mobility of dislocations was increased due to the increase in testing temperature.

The micro-hardness measurement results are shown in Table 3.

Table 3. Results of Micro-hardness measurements

Condition				
As cast		92.4		
Solution Hardened	102.5	103.2	103.3	

The solution hardening led to the increase of micro-hardness values.

## 4. Conclusions

The influence of solution hardening on microstructure and mechanical properties of Al-2.5 Mg-0.7Li alloy wereinvestigated. The solution hardening was performed in order to inducethe metastable Al3Li hardening precipitation and dissolving of ternary Al<sub>2</sub>LiMg intermetallic phase and secondary eutectic  $Al<sub>3</sub>Mg<sub>2</sub>$  phase and their incorporation in  $\alpha_{Al}$  solid solution.

However, samples tested in as cast condition showed the higher strength properties (Table 2). The texture developing during deformation was a result of interaction between Al3Li precipitates and dislocations progressing from the grain boundaries (Fig.1c). Although solution hardening has had a beneficial influence on micro-hardness values (Table 3), while at the same time having a weak influence on strength development. During deformation dislocations were moving freely, without limitation due to precipitations, resulting in low strength properties (Table 2). This is supported by lack of texture after deformation (Fig.1d).

#### 5. Acknowledgements

This research and paper are supported by the funds of the University of Zagreb within the framework of Financial Support for Research "Design and Characterization of Innovative Engineering Alloys", Code: TP167*.*

#### 6. References

[1] E. Aghion, B. Bronfin, D. Eliezer. (2001). The role of the magnesium industry in protecting the environment. Journal of Materials Processing Technology. 117(3),381- 385.

[2] S. Miller, L. Zhuang, J. Bottema, A. Wittebrood, P. Smet, A. Haszler, A. Vieregge.(2014). Recent development in aluminium alloys for the automotive industry.Materials Science and Engineering. 280(37), 7- 49.

[3] M. Uludağ, R. Çetin, D. Dispinar, M. Tiryakioğlu. (2017) Characterization of the Effect of Melt Treatments<br>on Melt Quality in Al-7wt %Si-Mg Alloys. in Al-7wt %Si-Mg Alloys. Materials.7(5), 157.

[4] R. J. Rioja, J. Liu. The Evolution of Al-Li Based Products for Aerospace and Space industry. (2012). Metallurgical and Materials Transactions A., 43 A, 3325- 3337